

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 1 of 64

Applicant: Shenzhen Huafurui Technology Co., Ltd
Address: Unit 1401 &1402, 14/F, Jinqi Zhigu Mansion (No. 4 Building of Chongwen Garden), Crossing of the Liuxian Street and Tangling Road, Taoyuan Street, Nanshan District, Shenzhen,P.R. China

The following sample was submitted and identified by/on behalf of the client as:

Sample Name: Smartphone
Model No.: X70
Trade Mark: CUBOT
Sample Received Date: 2023.04.23
Testing Period: 2023.04.23—2023.05.06
Test Requested: As specified by client, to screen the 233 substances of very high concern (SVHC) under Regulation (EC) No. 1907/2006 of REACH in the submitted sample(s).
Test Method: Please refer to the following page(s).
Test Result(s): Please refer to the following page(s).
Summary:


According to the ruling of the Court of Justice the European Union the definition of an article under REACH, and the specified scope and evaluation screening, the test result of SVHC are > 0.1% (w/w) in the articles of the submitted sample.	See remark for obligation under REACH
--	---------------------------------------

Checked by



Fang

Approved by



Ryan Zhang
Technical Manager



Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 2 of 64

Remark:

1. The chemical analysis of Specified SVHC is performed by means of currently available analytical techniques against the list published by ECHA. This list is under evaluation by ECHA and may subject to change in the future.
2. REACH regulations related to obligations
 - (a) The chemical analysis of SVHC is performed by means of currently available analytical Techniques against the list published by ECHA, and shall refer to <http://echa.europa.eu/web/guest/candidate-list-table>. This list is under evaluation by ECHA and may subject to change in the future;
 - (b) Concerning article(s):

Notification: In accordance with Regulation (EC) No 1907/2006, any producer or importer of articles shall notify ECHA, in accordance with paragraph 4 of Article 7, if a substance meets the criteria in Article 57 and is identified in accordance with Article 59(1) of the Regulation, if (i) the substance is present in those articles in quantities totaling over one ton ne per producer or importer per year; and (ii) the substance is present in those articles above a concentration of 0.1% weight by weight (w/w);

Inform: Article 33 of Regulation (EC) No 1907/2006 requires supplier of an article containing a substance meeting the criteria in Article 57 and identified in accordance with Article 59(1) in a concentration above 0.1% weight by weight (w/w) shall provide the recipient of the article with sufficient information, available to the supplier, to allow safe use of the article including, as a minimum, the name of that substance;
 - (c) Concerning material(s):

Test results in this report are based on the tested sample. This report refers to testing result of tested sample submitted as homogenous material(s). In case such material is being used to compose an article, the results indicated in this report may not represent SVHC concentration in such article. If this report refers to testing result of composite material group by equal weight proportion, the material in each composite test group may come from more than one article. If the sample is a substance or mixture, and it directly exports to EU, client has the obligation to comply with the supply chain communication obligation under Article 31 of Regulation (EC) No.1907/2006 and the conditions of Authorization of substance of very high concern included in the Annex XIV of the Regulation (EC) No. 1907/2006.
 - (d)Concerning substance and preparation:

If a SVHC is found over 0.1% (w/w) and/or the specific concentration limit which is set in Regulation (EC) No 1272/2008 and No 790/2009, client is suggested to prepare a Safety Data Sheet (SDS) against the SVHC to comply with the supply chain communication obligation under Regulation (EC) No 1907/2006.
3. If a SVHC is found over the reporting limit, client is suggested to identify the component which contains the SVHC and the exact concentration of the SVHC by requesting further quantitative analysis from the laboratory.

Test Method:

With reference to US EPA3052:1996, US EPA3050B:1996, US EPA3060A:1996, US EPA3550C:2007, US EPA3540C:1996, ISO17353:2004(E); Analysis was performed by GC-MS, ICP-OES, UV-Vis, HPLC-MS etc.

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 3 of 64

Test Result:

No.	Substance Name	CAS No.	Results (%)	RL(%)
001	All tested SVHC in candidate list	-	N.D.	-
002	All tested SVHC in candidate list	-	N.D.	-
003	All tested SVHC in candidate list	-	N.D.	-
004	All tested SVHC in candidate list	-	N.D.	-
005	All tested SVHC in candidate list	-	N.D.	-
006	All tested SVHC in candidate list	-	N.D.	-
007	1,3-propanesultone	1120-71-4	0.280	0.050
	Other tested SVHC in candidate list	-	N.D.	-
008	All tested SVHC in candidate list	-	N.D.	-
009	All tested SVHC in candidate list	-	N.D.	-
010	All tested SVHC in candidate list	-	N.D.	-
011	All tested SVHC in candidate list	-	N.D.	-

Material group:

- 001. Nonmetal group
- 002. Nonmetal group
- 003. Nonmetal group
- 004. Nonmetal group
- 005. Nonmetal group
- 006. Nonmetal group
- 007. Battery
- 008. Metal group
- 009. Metal group
- 010. Metal group
- 011. Glass

Group No.	Sample No.	Description
001	1	Black double-side tape
	2	Multi color plastic
	3	Black plastic with gun-color plating
	4	Black FPC
	5	Black FPC

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 4 of 64

	6	Black soft plastic
	7	Black foam tape
	8	Black soft plastic
	9	Yellow FPC
	10	Black material with magnetic properties
	11	Black plastic
	12	Transparent double-side tape
	13	Transparent plastic
	14	Black foam
	15	White paper label
	16	Black silica gel
	17	Silvery color textile tape
	18	Grey dry glue
	19	Black PCB
	20	Black plastic
002	21	Transparent plastic
	22	Silvery color double-side tape
	23	Yellow FPC
	24	Black plastic
	25	Black silica gel
	26	Black plastic jacket
	27	Red plastic jacket
	28	Black net fabric
	29	Black plastic
	30	Black plastic
	31	Transparent double-side tape
	32	Black plastic jacket
	33	White plastic jacket
	34	Red plastic jacket
	35	Blue plastic jacket
	36	Black soft plastic
	37	White plastic
	38	Green PCB
	39	Yellow FPC
	40	Transparent dry glue
003	41	Green PCB

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 5 of 64

	42	Yellow FPC
	43	Yellow transparent plastic tape
	44	Silvery color textile tape
	45	Black FPC
	46	Grey plastic
	47	Silvery color plastic
	48	Transparent plastic
	49	White translucent plastic
	50	Silvery color translucent plastic
	51	Silvery color translucent plastic
	52	Black plastic tape
	53	Yellow FPC
	54	Silvery color translucent plastic
	55	Black net fabric
	56	Black plastic
	57	White plastic
	58	Black plastic
	59	Grey plastic
	60	Transparent plastic
004	61	Green transparent plastic
	62	Black plastic
	63	Black FPC
	64	Black foam
	65	Yellow FPC
	66	Black soft plastic
	67	Black soft plastic
	68	Black plastic tape
	69	Black foam tape
	70	Yellow transparent plastic tape
	71	Transparent plastic
	72	Green paper
	73	Green dry glue
	74	Black FPC
	75	Black PCB
	76	White plastic
	77	White plastic

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 6 of 64

005	78	Black plastic
	79	White dry glue
	80	Green PCB
	81	White soft plastic
	82	Yellow plastic label
	83	White plastic cable jacket
	84	Black plastic jacket
	85	White plastic jacket
	86	Green plastic jacket
	87	Red plastic jacket
	88	White plastic
	89	White translucent dry glue
	90	White plastic
	91	Grey plastic
	92	Green PCB
	93	White plastic
	94	White soft plastic
95	White plastic jacket	
96	Copper color enamelled wire	
97	Blue-copper enamelled wire	
98	Blue enamelled wire	
99	Green enamelled wire	
100	Red enamelled wire	
006	101	White soft plastic
	102	White soft plastic
	103	Grey plastic
	104	Green PCB
	105	White soft plastic
	106	White plastic
	107	Blue PCB
	108	White plastic
	109	DK.blue net fabric
	110	Black net fabric
	111	White soft plastic
	112	White foam tape
	113	Transparent plastic film

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 7 of 64

	114	Green PCB
	115	White dry glue
	116	White net fabric
	117	Multi color plastic
007	118	Battery
008	119	Grey surfaced metal
	120	Silvery color metal screw with black coating
	121	Black surfaced metal
	122	Silvery color metal
	123	Black surfaced metal
	124	Silvery color metal
	125	Silvery color metal screw
	126	Silvery color metal
	127	Silvery color metal
	128	Silvery color metal wire core
	129	Silvery color metal
	130	Copper color enamelled wire
	131	Silvery color magnet
	132	Silvery color metal
	133	Copper color metal nut
	134	Copper color metal
	135	Silvery color metal
	136	Silvery color magnet
	137	Copper color metal
	138	Silvery color metal
009	139	Copper color enamelled wire
	140	Silvery color metal
	141	Silvery color metal
	142	Silvery color metal with black coating
	143	Copper color metal
	144	Copper color metal
	145	Silvery color metal
	146	Silvery color metal
	147	Silvery color magnet
	148	Copper color enamelled wire
	149	Copper color metal with black coating

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 8 of 64

	150	Copper color metal
	151	Silvery color metal
	152	Silvery color metal
	153	Copper color metal wire core
010	154	Silvery color metal
	155	Silvery color metal pin
	156	Silvery color metal
	157	Silvery color metal
	158	Silvery color metal pin
	159	Silvery color metal
	160	Silvery color metal
	161	Silvery color metal pin
	162	Silvery color metal
	163	Silvery color magnet
	164	Silvery color metal
	165	Copper color enamelled wire
	166	Silvery color metal
011	167	Transparent glass with black coating
	168	Transparent glass
	169	Black glass screen
	170	Transparent glass

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 9 of 64

- Note:
- 1.- RL = Report Limit
 2. -N.D. = Not Detected (<report limit)
 3. -0.1%= 1000 mg/kg =1000 ppm
 4. -*: Concentration value of the substance by the conversion from the test results of certain elements. Concentration value of Bis(tributyltin)oxide by the conversion from the test results of Tributyl Tins.
 5. -**:All refractory ceramic fibres are covered by index number 650-017-00-8 in Annex VI of the Regulation on Classification, Labeling and Packaging of chemical substances and mixtures, the so called CLP Regulation (Regulation (EC) No 1272/2008).
 6. -***: C.I.: Colour Index
 7. -****:Light fractions from distillation
 8. -*****:Concentration value of Disodium tetraborate, anhydrous and Tetraboron disodium heptaoxide, hydrate is evaluated by Disodium tetraborate, with no consider of the hydrate.
 9. -^①:In view of the substances are established as UVCB substances (substances of unknown or variable composition, complex reaction products or biological materials) consisting of different and variable constituents, the test results are calculated based on the main constituents of the representative compounds for substances.
 10. -^②:In view of the substance contain variable substances, the test results are calculated based on main constituents of the representative compounds for the substances, and the test results of the representative compounds are calculated based on the result of specified heavy metal elements.
 11. -^③:Concentration value of Boric acid; Disodium tetraborate, anhydrous; Tetraboron disodium heptaoxide, hydrate; Diboron trioxide; Sodium peroxometaborate; Sodium perborate; perboric acid, sodium salt are calculated by the conversion from the test results of certain elements and confirmed by appropriate solvent extraction, meanwhile the book of materials is suggested to be checked for further confirmation.
 12. As specified by client, the submitted sample were weight equal proportion mixed to test, the test results are calculated based on the minimum sample weight.


Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 10 of 64

Photo(s) of the sample(s)




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 11 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 12 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 13 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 14 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 15 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 16 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 17 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 18 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 19 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 20 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 21 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 22 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 23 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 24 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 25 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 26 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 27 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 28 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 29 of 64



Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 30 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 31 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 32 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 33 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 34 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 35 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 36 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 37 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 38 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 39 of 64



Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 40 of 64



Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 41 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 42 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 43 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 44 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 45 of 64



Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 46 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 47 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 48 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 49 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 50 of 64





Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 51 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 52 of 64




Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 53 of 64




Test Report


Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 54 of 64



Analytical flow chart of SVHC



Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 55 of 64

Appendix - Full list of tested SVHC

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
I	1	Anthracene	120-12-7	204-371-1	0.05%
I	2	4,4'- Diaminodiphenylmethane(MDA)	101-77-9	202-974-4	0.05%
I	3	Dibutyl phthalate(DBP)	84-74-2	201-557-4	0.05%
I	4	Cobalt dichloride*	7646-79-9	231-589-4	0.01%
I	5	Diarsenic pentaoxide*	1303-28-2	215-116-9	0.01%
I	6	Diarsenic trioxide*	1327-53-3	215-481-4	0.01%
I	7	Sodium dichromate*	7789-12-0/ 10588-01-9	234-190-3	0.01%
I	8	Musk xylene	81-15-2	201-329-4	0.05%
I	9	Bis(2-ethyl(hexyl)phthalate)(DEHP)	117-81-7	204-211-0	0.05%
I	10	Hexabromocyclododecane (HBCDD)	25637-99-4/ 3194-55-6	247-148-4/ 221-695-9	0.05%
I	11	Short Chain Chlorinated Paraffins(SCCPs)	85535-84-8	287-476-5	0.05%
I	12	Bis(tributyltin)oxide (TBTO)*	56-35-9	200-268-0	0.05%
I	13	Lead hydrogen arsenate*	7784-40-9	232-064-2	0.01%
I	14	Benzyl butyl phthalate(BBP)	85-68-7	201-622-7	0.05%
I	15	Triethyl arsenate*	15606-95-8	427-700-2	0.01%
II	16	^① Anthracene oil	90640-80-5	292-602-7	0.05%
II	17	^① Anthracene oil,anthracene paste, distn. Lights****	91995-17-4	295-278-5	0.05%
II	18	^① Anthracene oil, anthracene paste, anthracene fraction	91995-15-2	295-275-9	0.05%
II	19	^① Anthracene oil, anthracene-low	90640-82-7	292-604-8	0.05%
II	20	^① Anthracene oil, anthracene paste	90640-81-6	292-603-2	0.05%
II	21	^① Coal tar pitch, high temperature	65996-93-2	266-028-2	0.05%
II	22	Acrylamide	79-06-1	201-173-7	0.05%
II	23	2,4-Dinitrotoluene	121-14-2	204-450-0	0.05%
II	24	Diisobutyl phthalate (DIBP)	84-69-5	201-553-2	0.05%
II	25	^② Lead chromate	7758-97-6	231-846-0	0.05%
II	26	^② Lead chromate molybdate sulphate red(C.I. Pigment Red 104)***	12656-85-8	235-759-9	0.05%
II	27	^② Lead sulfochromate yellow(C.I. Pigment Yellow 34)***	1344-37-2	215-693-7	0.05%
II	28	Tris(2-chloroethyl)phosphate (TCEP)	115-96-8	204-118-5	0.05%
III	29	Trichloroethylene	79-01-6	201-167-4	0.05%
III	30	^③ Boric acid	10043-35-3 11113-50-1	233-139-2 234-343-4	0.01%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 56 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
III	31	③Disodium tetraborate, anhydrous****	1330-43-4 12179-04-3 1303-96-4	215-540-4	0.01%
III	32	③Tetraboron disodium heptaoxide, hydrous****	12267-73-1	235-541-3	0.01%
III	33	Sodium chromate*	7775-11-3	231-889-5	0.01%
III	34	Potassium chromate*	7789-00-6	232-140-5	0.01%
III	35	Ammonium dichromate*	7789-09-5	232-143-1	0.01%
III	36	Potassium dichromate*	7778-50-9	231-906-6	0.01%
IV	37	Cobalt(II) sulphate*	10124-43-3	233-334-2	0.01%
IV	38	Cobalt(II) dinitrate*	10141-05-6	233-402-1	0.01%
IV	39	Cobalt(II) carbonate*	513-79-1	208-169-4	0.01%
IV	40	Cobalt(II) diacetate*	71-48-7	200-755-8	0.01%
IV	41	2-Methoxyethanol	109-86-4	203-713-7	0.05%
IV	42	2-Ethoxyethanol	110-80-5	203-804-1	0.05%
IV	43	Chromium trioxide*	1333-82-0	215-607-8	0.01%
IV	44	①Chromic acid, Dichromic acid, Oligomers of chromic acid and dichromic acid*	7738-94-5 13530-68-2	231-801-5 236-881-5	0.01%
V	45	2-ethoxyethyl acetate	111-15-9	203-839-2	0.01%
V	46	Strontium chromate*	7789-06-2	232-142-6	0.01%
V	47	①1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters	68515-42-4	271-084-6	0.01%
V	48	Hydrazine	7803-57-8 302-01-2	206-114-9	0.05%
V	49	1-methyl-2-pyrrolidone	872-50-4	212-828-1	0.05%
V	50	1,2,3-trichloropropane	96-18-4	202-486-1	0.05%
V	51	①1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich	71888-89-6	276-158-1	0.05%
VI	52	Dichromium tris(chromate)*	24613-89-6	246-356-2	0.01%
VI	53	Potassium hydroxyoctaoxodizincatedichromate*	11103-86-9	234-329-8	0.01%
VI	54	Pentazinc chromate octahydroxide*	49663-84-5	256-418-0	0.01%
VI	55	②Aluminosilicate Refractory Ceramic Fibres (RCF)**	-	-	0.05%
VI	56	②Zirconia Aluminosilicate Refractory Ceramic Fibres(Zr-RCF)**	-	-	0.05%
VI	57	②Formaldehyde, oligomeric reaction products with aniline	25214-70-4	500-036-1	0.05%
VI	58	Bis(2-methoxyethyl) phthalate	117-82-8	204-212-6	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 57 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
VI	59	2-Methoxyaniline; o-Anisidine	90-04-0	201-963-1	0.05%
VI	60	4-(1,1,3,3-tetramethylbutyl)phenol (4-tert-Octylphenol)	140-66-9	205-426-2	0.05%
VI	61	1,2-Dichloroethane	107-06-2	203-458-1	0.05%
VI	62	Bis(2-methoxyethyl) ether	111-96-6	203-924-4	0.05%
VI	63	Arsenic acid*	7778-39-4	231-901-9	0.01%
VI	64	Calcium arsenate*	7778-44-1	231-904-5	0.01%
VI	65	Trilead diarsenate*	3687-31-8	222-979-5	0.01%
VI	66	N,N-dimethylacetamide	127-19-5	204-826-4	0.05%
VI	67	Phenolphthalein	77-09-8	201-004-7	0.05%
VI	68	2,2'-dichloro-4,4'-methylenedianiline (MOCA)	101-14-4	202-918-9	0.05%
VI	69	Lead diazide*	13424-46-9	236-542-1	0.01%
VI	70	Lead styphnate*	15245-44-0	239-290-0	0.01%
VI	71	Lead dipicrate*	6477-64-1	229-335-2	0.01%
VII	72	1,2-bis(2-methoxyethoxy)ethane	112-49-2	203-977-3	0.05%
VII	73	1,2-dimethoxyethane; ethylene glycol dimethyl ether (EGDME)	110-71-4	203-794-9	0.05%
VII	74	[®] Diboron trioxide	1303-86-2	215-125-8	0.01%
VII	75	Formamide	75-12-7	200-842-0	0.05%
VII	76	Lead(II) bis(methanesulfonate)*	17570-76-2	401-750-5	0.01%
VII	77	TGIC(1,3,5-tris(oxiranylmethyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione)	2451-62-9	219-514-3	0.05%
VII	78	β-TGIC (1,3,5-tris[(2S and2R)-2,3-epoxypropyl]-1,3,5-triazine-2,4,6-(1H,3H,5H)-trione)	59653-74-6	423-400-0	0.05%
VII	79	4,4'-bis(dimethylamino) benzophenone (Michler's ketone)	90-94-8	202-027-5	0.05%
VII	80	N,N,N',N'-tetramethyl-4,4'-methylenedianiline (Michler's base)	101-61-1	202-959-2	0.05%
VII	81	C.I. Basic Violet 3	548-62-9	208-953-6	0.05%
VII	82	C.I. Basic Blue 26	2580-56-5	219-943-6	0.05%
VII	83	C.I. Solvent Blue 4	6786-83-0	229-851-8	0.05%
VII	84	4,4'-bis(dimethylamino)-4''-(methylamino)trityl alcohol	561-41-1	209-218-2	0.05%
VIII	85	[Phthalato(2-)]dioxotrilead*	69011-06-9	273-688-5	0.01%
VIII	86	[®] 1,2-Benzenedicarboxylic acid, dipentylester, branched and linear	84777-06-0	284-032-2	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 58 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
VIII	87	1,2-Diethoxyethane	629-14-1	211-076-1	0.05%
VIII	88	1-Bromopropane	106-94-5	203-445-0	0.05%
VIII	89	3-Ethyl-2-methyl-2-(3-methylbutyl)-1,3-oxazolidine	143860-04-2	421-150-7	0.05%
VIII	90	4-(1,1,3,3-Tetramethylbutyl)phenol, ethoxylated	-	-	0.05%
VIII	91	4,4'-Methylenedi-o-toluidine	838-88-0	212-658-8	0.05%
VIII	92	4,4'-Oxydianiline and its salts	101-80-4	202-977-0	0.05%
VIII	93	4-Aminoazobenzene	60-09-3	200-453-6	0.05%
VIII	94	4-Methyl-m-phenylenediamine	95-80-7	202-453-1	0.05%
VIII	95	^① 4-Nonylphenol, branched and linear	--	--	0.05%
VIII	96	6-Methoxy-m-toluidine	120-71-8	204-419-1	0.05%
VIII	97	Acetic acid, lead salt, basic*	51404-69-4	257-175-3	0.01%
VIII	98	Biphenyl-4-ylamine	92-67-1	202-177-1	0.05%
VIII	99	Bis(pentabromophenyl) ether (DecaBDE)	1163-19-5	214-604-9	0.05%
VIII	100	C,C'-azodi(formamide)	123-77-3	204-650-8	0.05%
VIII	101	Dibutyltin dichloride	683-18-1	211-670-0	0.05%
VIII	102	Diethyl sulphate	64-67-5	200-589-6	0.05%
VIII	103	Diisopentyl phthalate (DIPP)	605-50-5	210-088-4	0.05%
VIII	104	Dimethyl sulphate	77-78-1	201-058-1	0.05%
VIII	105	Dinoseb	88-85-7	201-861-7	0.05%
VIII	106	Dioxobis(stearato)trilead*	12578-12-0	235-702-8	0.01%
VIII	107	Fatty acids, C16-18, lead salts*	91031-62-8	292-966-7	0.01%
VIII	108	Furan	110-00-9	203-727-3	0.05%
VIII	109	Henicosafuoroundecanoic acid	2058-94-8	218-165-4	0.05%
VIII	110	Heptacosafuorotetradecanoic acid	376-06-7	206-803-4	0.05%
VIII	111	Cyclohexane-1,2-dicarboxylic anhydride, cis-cyclohexane-1,2-dicarboxylic anhydride,trans-cyclohexane-1,2-dicarboxylic anhydride	85-42-7 13149-00-3 14166-21-3	201-604-9 236-086-3 238-009-9	0.05%
VIII	112	Hexahydromethylphthalic anhydride, Hexahydro-4- methylphthalic anhydride, Hexahydro-1- methylphthalic anhydride, Hexahydro-3- methylphthalic anhydride	25550-51-0 19438-60-9 48122-14-1 57110-29-9	247-094-1 243-072-0 256-356-4 260-566-1	0.05%
VIII	113	Lead bis(tetrafluoroborate)*	13814-96-5	237-486-0	0.01%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 59 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
VIII	114	Lead cyanamidate*	20837-86-9	244-073-9	0.01%
VIII	115	Lead dinitrate*	10099-74-8	233-245-9	0.01%
VIII	116	Lead monoxide*	1317-36-8	215-267-0	0.01%
VIII	117	Lead oxide sulphate*	12036-76-9	234-853-7	0.01%
VIII	118	Lead tetroxide*	1314-41-6	215-235-6	0.01%
VIII	119	Lead titanium trioxide*	12060-00-3	235-038-9	0.01%
VIII	120	Lead Titanium Zirconium Oxide*	12626-81-2	235-727-4	0.01%
VIII	121	Methoxyacetic acid	625-45-6	210-894-6	0.05%
VIII	122	N,N-dimethylformamide	68-12-2	200-679-5	0.05%
VIII	123	N-methylacetamide	79-16-3	201-182-6	0.05%
VIII	124	N-pentyl-isopentyl phthalate	776297-69-9	-	0.05%
VIII	125	o-Aminoazotoluene	97-56-3	202-591-2	0.05%
VIII	126	o-Toluidine	95-53-4	202-429-0	0.05%
VIII	127	Pentacosafuorotridecanoic acid	72629-94-8	276-745-2	0.05%
VIII	128	Pentalead tetraoxide sulphate*	12065-90-6	235-067-7	0.01%
VIII	129	Propylene oxide	75-56-9	200-879-2	0.05%
VIII	130	Pyrochlore, antimony lead yellow*	8012-00-8	232-382-1	0.01%
VIII	131	Silicic acid, barium salt, lead-doped*	68784-75-8	272-271-5	0.01%
VIII	132	Silicic acid, lead salt*	11120-22-2	234-363-3	0.01%
VIII	133	Sulfurous acid, lead salt, dibasic*	62229-08-7	263-467-1	0.01%
VIII	134	Tetraethyllead*	78-00-2	201-075-4	0.01%
VIII	135	Tetralead trioxide sulphate*	12202-17-4	235-380-9	0.01%
VIII	136	Tricosafuorododecanoic acid	307-55-1	206-203-2	0.05%
VIII	137	Trilead bis(carbonate)dihydroxide*	1319-46-6	215-290-6	0.01%
VIII	138	Trilead dioxide phosphonate*	12141-20-7	235-252-2	0.01%
IX	139	Cadmium	7440-43-9	231-152-8	0.01%
IX	140	Cadmium oxide*	1306-19-0	215-146-2	0.01%
IX	141	Ammonium pentadecafluorooctanoate(APFO)	3825-26-1	223-320-4	0.05%
IX	142	Pentadecafluorootanoic acid(PFOA)	335-67-1	206-397-9	0.05%
IX	143	Dipentyl phthalate(DPP)	131-18-0	205-017-9	0.05%
IX	144	4-Nonlphenol, branched and linear, ethoxylated	-	-	0.05%
X	145	Cadmium sulphide*	1306-23-6	215-147-8	0.01%
X	146	Dihexyl phthalate	84-75-3	201-559-5	0.05%
X	147	C.I. Direct Red 28	573-58-0	209-358-4	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 60 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
X	148	C.I. Direct Black 38	1937-37-7	217-710-3	0.05%
X	149	Imidazolidine-2-thione; 2-imidazoline-2-thiol	96-45-7	202-506-9	0.05%
X	150	Lead di(acetate)*	301-04-2	206-104-4	0.01%
X	151	®Trixylyl phosphate	25155-23-1	246-677-8	0.05%
XI	152	Cadmium chloride*	10108-64-2	233-296-7	0.01%
XI	153	1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear	68515-50-4	271-093-5	0.05%
XI	154	®Sodium peroxometaborate	7632-04-4	231-556-4	0.01%
XI	155	®Sodium perborate; perboric acid, sodium salt	-	239-172-9 234-390-0	0.01%
XII	156	2-(2H-benzotriazol-2-yl)-4,6-ditertpentylphenol (UV-328)	25973-55-1	247-384-8	0.05%
XII	157	2-benzotriazol-2-yl-4,6-di-tert-butylphenol (UV-320)	3846-71-7	223-346-6	0.05%
XII	158	Cadmium fluoride*	7790-79-6	232-222-0	0.01%
XII	159	Cadmium sulphate*	10124-36-4 31119-53-6	233-331-6	0.01%
XII	160	2-ethylhexyl 10-ethyl-4,4-dioctyl-7-oxo-8-oxa-3,5-dithia-4-stannatetradecanoate (DOTE)	15571-58-1	239-622-4	0.05%
XII	161	Reaction mass of 2-ethylhexyl 10-ethyl-4,4-dioctyl-7-oxo-8-oxa-3,5-dithia-4-stannatetradecanoate and 2-ethylhexyl 10-ethyl-4-[[2-[(2-ethylhexyl)oxy]-2-oxoethyl]thio]-4-octyl-7-oxo-8-oxa-3,5-dithia-4-stannatetradecanoate (reaction mass of DOTE and MOTE)	-	-	0.05%
XIII	162	1,2-benzenedicarboxylic acid, di-C6-10-alkyl esters; 1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with ≥ 0.3% of dihexyl phthalate (EC No. 201-559-5)	68515-51-5 68648-93-1	271-094-0 272-013-1	0.05%
XIII	163	5-sec-butyl-2-(2,4-dimethylcyclohex-3-en-1-yl)-5-methyl-1,3-dioxane [1], 5-sec-butyl-2-(4,6-dimethylcyclohex-3-en-1-yl)-5-methyl-1,3-dioxane [2] [covering any of the individual isomers of [1] and [2] or any combination thereof]	-	-	0.05%
XIV	164	1,3-propanesultone	1120-71-4	214-317-9	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 61 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
XIV	165	2,4-di-tert-butyl-6-(5-chlorobenzotriazol-2-yl)phenol (UV-327)	3864-99-1	223-383-8	0.05%
XIV	166	2-(2H-benzotriazol-2-yl)-4-(tert-butyl)-6-(sec-butyl)phenol (UV-350)	36437-37-3	253-037-1	0.05%
XIV	167	Nitrobenzene	98-95-3	202-716-0	0.05%
XIV	168	Perfluorononan-1-oic acid (2,2,3,3,4,4,5,5,6,6,7,7,8,8,9,9,9-heptadecafluorononanoic acid and its sodium and ammonium salts)	375-95-1 21049-39-8 4149-60-4	206-801-3	0.05%
XV	169	Benzo[def]chrysene	50-32-8	200-028-5	0.05%
XVI	170	4,4'-Isopropylidenediphenol (Bisphenol A)	80-05-7	201-245-8	0.05%
XVI	171	4-Heptylphenol, branched and linear [substances with a linear and/or branched alkyl chain with a carbon number of 7 covalently bound predominantly in position 4 to phenol, covering also UVCB- and well-defined substances which include any of the individual isomers or a combination thereof]	1987-50-4 72624-02-3	217-862-0	0.05%
XVI	172	p-(1,1-dimethylpropyl)phenol	80-46-6	201-280-9	0.05%
XVI	173	Nonadecafluorodecanoic acid (PFDA) and its sodium and ammonium salts	3108-42-7 335-76-2 3830-45-3	- 206-400-3 221-470-5	0.05%
XVII	174	Perfluorohexane-1-sulphonic acid and its salts (PFHxS)	70225-16-0 3871-99-6 355-46-4 68259-08-5	274-462-9 223-393-2 206-587-1 269-511-6	0.05%
XVIII	175	Benz[a]anthracene	56-55-3	200-280-6	0.05%
XVIII	176	Cadmium nitrate	10325-94-7	233-710-6	0.01%
XVIII	177	Cadmium carbonate	513-78-0	244-168-5	0.01%
XVIII	178	Cadmium hydroxide	21041-95-2	208-168-9	0.01%
XVIII	179	Chrysene	218-01-9	205-923-4	0.05%
XVIII	180	Reaction products of 1,3,4-thiadiazolidine-2,5-dithione, formaldehyde and 4-heptylphenol, branched and linear (RP-HP)	939-00-9	300-298-5 939-460-0	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 62 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
XVIII	181	1,6,7,8,9,14,15,16,17,17,18,18-Dodecacycloropentacyclo[12.2.1.16,9.02,13.05,10]octadeca-7,15-diene ("Dechlorane Plus"™)(including any of its individual anti- and syn-isomers or any combination thereof)	-	-	0.05%
XIX	182	Terphenyl, hydrogenated	61788-32-7	262-967-7	0.05%
XIX	183	Octamethylcyclotetrasiloxane(D4)	556-67-2	209-136-7	0.05%
XIX	184	Lead*	7439-92-1	231-100-4	0.01%
XIX	185	Ethylenediamine(EDA)	107-15-3	203-468-6	0.05%
XIX	186	Dodecamethylcyclohexasiloxane(D6)	540-97-6	208-762-8	0.05%
XIX	187	Disodium octaborate	12008-41-2	234-541-0	0.05%
XIX	188	Dicyclohexyl phthalate(DCHP)	84-61-7	201-545-9	0.05%
XIX	189	Decamethylcyclopentasiloxane(D5)	541-02-6	208-764-9	0.05%
XIX	190	Benzo[ghi]perylene	191-24-2	205-883-8	0.05%
XIX	191	Benzene-1,2,4-tricarboxylic acid 1,2 anhydride(TMA)	552-30-7	209-008-0	0.05%
XX	192	Pyrene	129-00-0	204-927-3	0.05%
XX	193	Phenanthrene	85-01-8	201-581-5	0.05%
XX	194	Fluoranthene	206-44-0 93951-69-0	205-912-4	0.05%
XX	195	Benzo[k]fluoranthene	207-08-9	205-916-6	0.05%
XX	196	2,2-bis(4'-hydroxyphenyl)-4-methylpentane	6807-17-6	401-720-1	0.05%
XX	197	1,7,7-trimethyl-3-(phenylmethylene)bicyclo[2.2.1]heptan-2-one	15087-24-8	239-139-9	0.05%
XXI	198	2,3,3,3-tetrafluoro-2-(heptafluoropropoxy)propionic acid, its salts and its acyl halides	-	-	0.05%
XXI	199	2-methoxyethyl acetate	110-49-6	203-772-9	0.05%
XXI	200	4-tert-butylphenol	98-54-4	202-679-0	0.05%
XXI	201	Tris(4-nonylphenyl, branched and linear) phosphite (TNPP) with $\geq 0.1\%$ w/w of 4-nonylphenol, branched and linear (4-NP)	26523-78-4 3050-88-2	247-759-6 608-492-4 701-028-2	0.05%
XXII	202	Perfluorobutane sulfonic acid (PFBS) and its salts	-	-	0.05%
XXII	203	Diisohexyl phthalate	71850-09-4	276-090-2	0.05%
XXII	204	2-methyl-1-(4-methylthiophenyl)-2-morpholinopropan-1-one	71868-10-5	400-600-6	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 63 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
XXII	205	2-benzyl-2-dimethylamino-4'-morpholinobutyrophenone	119313-12-1	404-360-3	0.05%
XXIII	206	1-vinylimidazole	1072-63-5	214-012-0	0.05%
XXIII	207	2-methylimidazole	693-98-1	211-765-7	0.05%
XXIII	208	butyl 4-hydroxybenzoate	94-26-8	202-318-7	0.05%
XXIII	209	Dibutylbis(pentane-2,4-dionato-O,O')tin	22673-19-4	245-152-0	0.05%
XXIV	210	bis(2-(2-methoxyethoxy)ethyl) ether	143-24-8	205-594-7	0.05%
XXIV	211	Diocetyl tin dilaurate, stannane, dioctyl-, bis(coco acyloxy) derivs., and any other stannane, dioctyl-, bis(fatty acyloxy) derivs. wherein C12 is the predominant carbon number of the fatty acyloxy moiety	-	-	0.05%
XXV	212	1,4-dioxane	123-91-1	204-661-8	0.05%
XXV	213	2,2-bis(bromomethyl)propane-1,3-diol (BMP) 2,2-dimethylpropan-1-ol, tribromo derivative/3-bromo-2,2-bis(bromomethyl)-1-propanol (TBNPA) 2,3-dibromo-1-propanol (2,3-DBPA)	3296-90-0 36483-57-5 1522-92-5 96-13-9	221-967-7 253-057-0 - 202-480-9	0.05%
XXV	214	2-(4-tert-butylbenzyl)propionaldehyde and its individual stereoisomers	-	-	0.05%
XXV	215	4,4'-(1-methylpropylidene) bisphenol (bisphenol B)	77-40-7	201-025-1	0.05%
XXV	216	Glutaral	111-30-8	203-856--5	0.05%
XXV	217	Medium-chain chlorinated paraffins (MCCP) [UVCB substances consisting of more than or equal to 80% linear chloroalkanes with carbon chain lengths within the range from C14 to C17]	-	-	0.05%
XXV	218	Orthoboric acid, sodium salt	13840-56-7	237-560-2	0.01%
XXV	219	Phenol, alkylation products (mainly in para position) with C12-rich branched or linear alkyl chains from oligomerisation, covering any individual isomers and/ or combinations thereof (PDDP)	-	-	0.05%

Test Report

Report No. : TCT230423C069

Date : May. 06, 2023

Page No.: 64 of 64

Batch	No.	Substance Name(s)	CAS No.	EC No.	RL
XXVI	220	(±)-1.7.7-trimethyl-3-[(4-methylphenyl)methylene] bicyclo[2.2.1]heptan-2-one covering any of the individual isomers and/or combinations thereof(4-MBC)	-	-	0.05%
XXVI	221	6,6'-di-tert-butyl-2,2'-methylenedi-p-cresol (DBMC)	119-47-1	204-327-1	0.05%
XXVI	222	S-(tricyclo[5.2.1.0' ² .6]deca-3-en-8(or 9)-yl O-(isopropyl or isobutyl or 2-ethylhexyl) O-(isopropyl or isobutyl or 2-ethylhexyl) phosphorodithioate	255882-94-8	401-850-9	0.05%
XXVI	223	tris(2-methoxyethoxy)vinsilane	1067-53-4	213-934-0	0.05%
XXVII	224	N-(hydroxymethyl)acrylamide	924-42-5	213-103-2	0.05%
XXVIII	225	1,1'-[ethane-1,2-diylbisoxy]bis[2,4,6-tribromobenzene] (BTBPE)	37853-59-1	253-692-3	0.05%
XXVIII	226	2,2',6,6'-tetrabromo-4,4'-isopropylidenediphenol (TBBPA)	79-94-7	201-236-9	0.05%
XXVIII	227	4,4'-sulphonyldiphenol (BPS)	80-09-1	201-250-5	0.05%
XXVIII	228	Barium diboron tetraoxide"	13701-59-2	237-222-4	0.01%
XXVIII	229	Bis(2-ethylhexyl) Tetrabromophthalate covering any of the individual isomers and/or combinations thereof (TBPH)	-	-	0.05%
XXVIII	230	Isobutyl 4-hydroxybenzoate	4247-02-3	224-208-8	0.05%
XXVIII	231	Melamine	108-78-1	203-615-4	0.05%
XXVIII	232	Perfluoroheptanoic acid (PFHpA) and its salts	-	-	0.05%
XXVIII	233	Reaction mass of 2,2,3,3,5,5,6,6-octafluoro-4-(1,1,1,2,3,3,3-heptafluoropropan-2-yl)morpholine and -octafluoro-4-(heptafluoropropyl)morpholine	-	473-390-7	0.05%

*** End of Report ***

Remark: This report is considered invalidated without the Special Seal for Inspection of the TCT. This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of TCT, this test report shall not be copied except in full and published as advertisement.